



Chantelle

Applications	Gardens, Terraces, Trade fairs, Hotels, etc...
Fibres	70% Polyethylene/ 30% Polypropylene/ UV-Stabilized/ dtex 10700 Nerved ellipse shape Straight & Curled
Production method	Linear tufting
Gauge	3/8"
# stitches / lm	ca. 150 / lm
# tufts / m ²	ca. 15.750 / m ²
# filaments / m ²	ca. 504.000 / m ²
Pile height	ca. 30 mm
Pile weight	ca. 1500 gr / m ²
Total height	ca. 32 mm
Total weight	ca. 2635 gr / m ²
Tuft cloth	Polypropylene, ca. 135 gr / m ²
Backing	Latex, ca. 1000 gr / m ²
Infill	/
Roll width	400 cm
Colour	Green
Colour fastness	Scale 7 (DIN 54004)
UV-Stability	> 3.000 hours UV-A
Chlore resistance	6.10-4 m/sec
Resistance to sea water	+/- 30 N
Water permeability	6.10-4 m/sec
Pile anchorage	> 30 N

Namgrass reserves the right to amend technical specifications on the above mentioned product. Delivered products can slightly differ from these technical data. Namgrass guarantees the technical quality of the proposed article.